COROD® D-Grade Carbon Steel (D/DR) Continuous Rod

Weatherford's *COROD* D-grade carbon steel (D/DR) continuous rod is designed for medium-load reciprocating-rod and rotary-rod pumping in wells that are noncorrosive or mildly corrosive but effectively inhibited. This product is available in multiple round and semi-elliptical sizes to suit a wide range of applications.

COROD continuous rod provides a superior alternative to conventional sucker rods. Unlike conventional sucker rods, which are coupled every 25 or 30 ft (7.6 or 9.1 m), *COROD* continuous rod requires couplings only at the top and bottom of the rod string, regardless of well depth. This innovative solution reduces pin and coupling failures by decreasing the number of threaded connections, thereby minimizing the potential for rod string failures and costly well interventions. With more uniform contact loads and a lighter weight that reduces torque and power requirements for rotary-based applications, *COROD* continuous rod also extends the lifespan of tubing. Installation is quick, and Weatherford offers a full array of field servicing options.

Applications

- Rotary (progressing cavity pumping) systems
- Reciprocating-rod-lift systems

Features, Advantages and Benefits

- Fewer threaded connections on the rod string reduce the potential for pin and coupling failures as well as the need for costly well interventions.
- The uniform body design evenly distributes contact loads over the entire rod, reducing the severity of tubing and rod wear.
- The large annular space minimizes pressure losses.
- The rod strings are lighter than conventional sucker-rod strings, reducing the amount of weight on the service unit.

© 2011-2012 Weatherford. All rights reserved.

COROD® D-Grade Carbon Steel (D/DR) Continuous Rod

Specifications

Minimum tensile strength (psi/*MPa*)	115,000 *790*
Minimum yield strength (psi/*MPa*)	85,000 *590*
Maximum average hardness	Rockwell: 28 Brinell: 271
Heat treatment	Quenched and tempered

Chemical Composition

Note: all elements in % by weight

Material	Carbon	Manganese	Phosphorus Maximum	Sulphur Maximum	Silicon	Nickel Maximum	Chromium Maximum	Molybdenum Maximum	Aluminum	Titanium	Copper Maximum
1536 M	0.31 to 0.35	1.10 to 1.30	0.015	0.010	0.15 to 0.35	0.25	0.25	0.050	0.020 to 0.050	—	0.35

© 2011-2012 Weatherford. All rights reserved.

COROD® D-Grade Carbon Steel (D/DR) Continuous Rod

Product Types

Round

(Rotary and reciprocating applications)

COROD Number	*COROD* Size (in./*mm*)	Minimum Weight (lb/ft, *kg/m*)	Minimum Area (in.²/*mm²*)	Maximum Torque (ft lb/*N•m*)
DR 8.5	1-5/32 *29.4*	3.57 *5.32*	1.050 *678*	1,490 *2,020*
DR 6	1 *25.4*	2.67 *3.98*	0.785 *507*	955 *1,295*
DR 4	7/8 *22.2*	2.04 *3.05*	0.601 *388*	640 *868*
DR 3	13/16 *20.6*	1.76 *2.63*	0.518 *335*	500 *678*

Semi-Elliptical

(Reciprocating applications)



COROD Number	*COROD* Size (in./*mm*)	Minimum Weight (lb/ft, *kg/m*)	Minimum Area (in.²/*mm²*)
D 8	1-1/8 *28.6*	3.38 *5.03*	0.994 *642*
D 7	17/16 *27.0*	3.01 *4.49*	0.886 *572*
D 6	1 *25.4*	2.67 *3.98*	0.785 *507*
D 5	15/16 *23.8*	2.35 *3.50*	0.690 *445*
D 4	7/8 *22.2*	2.04 *3.05*	0.601 *388*
D 3	13/16 *20.6*	1.76 *2.63*	0.518 *335*
D 2	3/4 *19.0*	1.50 *2.24*	0.442 *285*

© 2011-2012 Weatherford. All rights reserved. 7846.01

Weatherford products and services are subject to the Company's standard terms and conditions, available on request or at weatherford.com. For more information contact an authorized Weatherford representative. Unless noted otherwise, trademarks and service marks herein are the property of Weatherford and may be registered in the United States and/or other countries. Weatherford products named herein may be protected by one or more U.S. and/or foreign patents. For more information, contact patents@weatherford.com. Specifications are subject to change without notice. Weatherford sells its products and services in accordance with the terms and conditions set forth in the applicable contract between Weatherford and the client.